

Product Information Construction Sealants

DOW CORNING

Dow Corning® Silicone Glazing Sealant

FEATURES & BENEFITS

- Cures to 100% silicone rubber
- Resistant to sunlight and weather extremes
- High strength, excellent adhesion
- Remains flexible, will not become brittle, crack, shrink or chalk
- Bonds to many common substrates
- Supplied in removable, reusable, resealable nozzle that saves time and sealant

COMPOSITION

- One-part, acetoxy-cure, RTV silicone

Professional quality sealant specifically formulated to meet glass shop glazing needs

APPLICATIONS

- General glazing applications, backlite replacement and skylight installations
- Repairing weatherstripping and gaskets
- Sealing most glass, plastics, metal, repainted surfaces, fiberglass, ceramics and aluminum substrates

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Test	Unit	Result
Tooling Time ¹	minutes	< 10
Tack-Free Time ¹	minutes	10-15
Complete Set-Up Time ¹ , 1/8"	hours	24
Cure System		Acetoxy
Application Temperature Range	°F (°C)	-20 to 122 (-29 to 50)
VOC Content ²	g/L	22
As Cured – After 7 days		
Durometer Hardness Shore A	points	26
Tensile Strength	psi	251
Elongation	percent	470
Temperature Range (Continuous)	°F (°C)	-40 to 350 (-40 to 176)
Movement Capability	percent	±25

¹At 25°C (77°F) and 50% relative humidity.

²Based on South Coast Air Quality Management District of California. Maximum VOC is listed both inclusive and exclusive of water and exempt compounds. For a VOC data sheet for a specific sealant color, please send your request to product.inquiry@dowcorning.com.

DESCRIPTION

Dow Corning® Silicone Glazing Sealant is a professional quality sealant specifically formulated to meet glass shop glazing needs. It forms a long-lasting, water-resistant seal with ±25% movement capability when properly applied. Its unique adhesion-promoted formulation ensures adhesion to many building substrates, and longer working time means a

professional appearance for the finished job.

Dow Corning Silicone Glazing Sealant meets the requirements of:

- ASTM C920 Type S, Grade NS, Class 25, Use NT, G and A
- TT-S-001543A
- TT-S-00230C, Class A (COM-NBS)

Dow Corning Silicone Glazing Sealant (translucent white) meets the requirements of:

- ASTM C920 Type S, Grade NS, Class 25, Use NT, G and A
- TT-S-001543A
- TT-S-00230C

HOW TO USE

1. **Refer** to product packaging for use-by date.
2. **Temperature.** Apply sealant at temperatures between -20 and 122°F (-29 and 50°C) for best results.
3. **Prepare surface.** Cut out and remove all old caulk for repair applications.
4. **Clean, Two-Step.** First, apply solvent to a lint-free cloth and vigorously wipe bonding surfaces to remove dirt and residues. Next, use a dry wipe to remove remaining solvent and residue for optimum cleaning. Repeat if necessary. Surfaces must be clean, dry, oil- and frost-free for best results. (Recommended solvents include isopropyl alcohol, toluene, xylene, naphtha or similar solvent.) Always wear gloves and follow safety precautions and directions on solvent container. **DO NOT USE** gasoline or kerosene.
5. **Install.** Install back-up spacing material for better filling, especially if width exceeds 1/2" to maximize bonding results. Open-cell polyethylene foam backer rod can be used.
6. **Mask.** Apply masking tape to areas adjacent to the joint to ensure straight bead lines and easy cleanup. Remove masking tape immediately after the bead is completed and before a skin forms.
7. **Open cartridge.** Cut snub nose above threads, reattach and cut nozzle to desired size. Insert into a caulking gun.
8. **Apply.** Extrude sealant with a smooth, steady motion, and ensure complete fill of joint cavity before proceeding.
9. **Tool.** Tool the sealant immediately after application and before a skin forms. Remove masking immediately after tooling.

10. **Replace cartridge cap.** See "Usable Life and Storage" instructions.

Cleanup Instructions

1. Cleanup should start immediately after sealant has been applied/ tooling and masking tape removed.
2. While wearing solvent-resistant gloves, wipe off excess sealant from surfaces and tools with a solvent-moistened cloth within 10 minutes of application.
3. If excess sealant is completely cured, carefully cut or scrape away.
4. Avoid contact of uncured sealant with skin and clothing. If contact does occur, wipe with clean rags and wash with water.

HANDLING

PRECAUTIONS

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEBSITE AT DOW CORNING.COM, OR FROM YOUR DOW CORNING SALES APPLICATION ENGINEER, OR DISTRIBUTOR, OR BY CALLING DOW CORNING CUSTOMER SERVICE.

USABLE LIFE AND STORAGE

Product should be stored at or below 32°C (90°F) in original, unopened containers. The most up-to-date shelf life information can be found on the XIAMETER website in the Product Detail page under Sales Specification.

LIMITATIONS

- Not for structural glazing
- Not paintable
- Not suited for prolonged submersion in water or below-grade applications

- May not adhere to oily woods or be compatible with substrates made of methylmethacrylate, polycarbonate, polypropylene, polyethylene, and polytetrafluoroethylene
- Not suitable for surfaces that might bleed oils, plasticizers or solvents, or porous surfaces such as cementlike materials, stone or surfaces prone to attack by weak acids
- May not cure properly if used in spaces confined from atmospheric moisture
- May cause corrosion on some brass, copper, zinc or zinc alloy-containing fixtures
- Not for use where abrasion and physical abuse are encountered
- This product is neither tested nor represented as suitable for medical or pharmaceutical uses

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, dowcorning.com or consult your local Dow Corning representative.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customers' tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

TO THE FULLEST EXTENT PERMITTED BY APPLICABLE LAW, DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

*We help you invent the future.*TM

dowcorning.com