

PURfectseal® GUN FOAM



PURfectseal Gun Foam is a single-component, moisture-curing, low-expansion gun foam, which has good cold weather gun ability. It is specially formulated to be 'O-Zone' friendly and is extremely economical — ideal for weather applications down to -10°C.

■ FEATURES & TYPICAL USES:

Features:

- O-zone friendly
- Low expansion
- Economically priced

Basic uses include:

1. Sealing around windows & doors
2. General gap, crack, and crevice filling / sealing
3. Gap filling in retrofit construction

Bonds To:

- Most construction substrates
- Wood
- Metal
- Brick & mortar
- Concrete & stone
- Most plastics

■ SURFACE PREPARATION & APPLICATION:

Before Use: Read the label in its entirety.

Surface Preparation:

- Surfaces must be structurally sound, clean, dry, and free from oil, grease, frost, dirt, or any other material and membranes that may deter adhesion. Dampness will not impair bond.
- For maximum yield the temperature of the can and contents should be 20°C (68°F).

Application:

1. Ideal application temperature is 4°C (39°F). Colder temperatures lengthen curing time.
2. Follow all instructions on the label.
3. Fill gaps, cracks, crevices, and holes to 30% of volume with foam making allowance for post expansion.
4. Multiple layers will be necessary in large cavities, with successive layers being allowed to expand and cure before the next layer is applied.

Cure:

- Full cure time is between 12 - 24 hours.
- Cure time is affected by humidity, degree of confinement, and cross-sectional thickness of the material.

Clean-up:

1. Uncured PURfectseal Polyurethane Foam can be dissolved with UltraSeal® PF-10 Foam Cleaner
2. Alternatively use a cloth saturated with mineral spirits, acetone, or denatured alcohol to wipe away any remaining foam.
3. Clean surface with soap and water if possible.



ULTRA SEAL®
PU FOAMS

PURfectseal® GUN FOAM

■ TYPICAL PROPERTIES:

These values are not intended for use in preparing specifications. Spec Writers; please contact NUCO Inc. before writing specifications if any further information is required.

Description	Specification
As Supplied...	
Type:	One part polyurethane foam
Cure method:	Moisture cure
Application temperature range (°C (°F)):	-10° to 46°C (14° to 115°F)
Cure time 1/8" bead (25°C (77°F)) and 50% relative humidity:	12 - 24 hours
Tack free time:	~10 minutes
Cuttable (1" bead)	<1 hour
As Cured - Physical - after 7 days at 25°C (77°F) and 50% relative humidity...	
Density:	1.0 lbs./ft ³ (17.6 kg/m ³)

Disclosure: The information and data contained herein is BASED ON INFORMATION WE BELIEVE TO BE RELIABLE. Please read all statements, recommendations or suggestions herein in conjunction with our CONDITIONS of SALE which apply to all goods supplied by us. We assume no responsibility for the use of these statements, recommendations or suggestions, nor do we intend them as recommendation for any use which would infringe any patent or copyright.

■ LIMITATIONS:

- Do not use below-grade
- Cured foam should be protected against UV rays (i.e. sunlight) by painting or staining to prevent long term dis-colouration or degradation.

■ STORAGE AND SHELF LIFE:

- Shelf life is 12 months from the date of manufacture when stored in a clean, dry area.
- Store between 4° to 32°C (40° to 90°F).
- Do not allow material to freeze or exceed 49°C (120°F)

■ ADDITIONAL NOTES:

- When cured, polyurethane foam is permanent, non-toxic, chemically inert, non-reactive and stable for an indefinite period of time.

■ CAUTION:

- The propellant is extremely flammable during dispensing and cure. Provide cross-ventilation to remove any build-up of vapours.
- Contents under pressure.
- Do not place in hot water or near radiators, stoves or other sources of heat.
- Do not leave container in a closed area such as a motor vehicle, especially in the summer heat
- Avoid skin contact and DO NOT ingest.
- Consult Safety Data Sheet.

■ MANUFACTURER INFORMATION:

NUCO Inc. 150 Curtis Drive T: 519-823-4994
Guelph, ON N1K 1N5 F: 519-823-1099

TF: 1-800-853-3984
E: info@nucoinc.com

LIMITED WARRANTY INFO:

NUCO Inc., warrants only that its product will meet its specifications for a period of 12 months following date of manufacture. NUCO shall in no event be liable for incidental or consequential damage, or improper storage. NUCO's liability, expressed or implied is limited to the stated selling price of any goods found to be defective.

AVAILABLE SIZES & COLOURS:

SKU	Size	Volume
51900	820 g (29 oz.)	51 L (1.81 ft ³)

THEORETICAL YIELD: Approx. linear feet

	Joint Width		
	1/4"	3/8"	1/2"
820 g (29 oz.)	5,913 ft.	2,361 ft.	1,328 ft.

Yields are based on theoretical calculations for comparison purposes only & will vary depending on ambient conditions and particular applications.